

Features

Anti-Bacteria Treated
Blockout

Self-Clean
UV Resistant

Flame Retardant
Light Fastness

Applications



Technical Data Sheet

Item Code	T703	Test Method
Base Fabric	1000D*1000D 23*23	DIN EN ISO2060
Weight (GSM)	750	DIN EN ISO2286-2
Tensile Strength	Warp (N/5cm)	2500
	Weft (N/5cm)	2300
Tear Strength	Warp (N/5cm)	350
	Weft (N/5cm)	300
Peeling Strength	Warp (N/5cm)	100
	Weft (N/5cm)	100
Temperature	-30°C/+70°C	
Flame Retardant	B1/M1/M2/NFPA701	
Lacquering (Optional)	Acrylic/ PVDF	
Special Treatment	Anti-Wicking/Anti-UV/Anti-Aging/Cold Resistant/Osmosis Prevention/Mildew Resistant	

Information contained in this document is based on our general experience and is given in good faith. But we are unable to accept responsibility in respect to factors which are outside our knowledge or control.



Add: Room 912, No.3 Building, Shangdong Business Center, Haizhou District,
Haining, Zhejiang, China
Tel: +86-573-80776996 Fax: +86-573-80776998
Mob/Skype/Wechat: +86-15858322153
mailto:hncomax@163.com jeffcheung@hncomax.com

